

cracks in the framework of Linear Elastic Fracture Mechanics [4, 5], which has proven its validity for single straight crack dynamics in brittle materials [6, 7, 8]. The main goal of this approach is to obtain expressions for the stress intensity factors at the crack tips of the emergent bifurcated cracks. The idea is to compare their associated energy release rates with the unperturbed configuration, i.e. a crack from which no branches emanated. The dependence of these energy release rates in the crack kink angles, velocities, etc., may elucidate the origin of the instability. This line of work involves solving a dynamic linear elasticity problem where the crack boundaries develop a kinked shape that makes the theoretical analysis quite involved. Our final goal is to solve the problem of determining the stress intensity factors of a kinked crack that starts at a given angle and velocity from a main crack whose velocity is also given. The present work is an intermediate step towards that final goal.

The aim of this presentation is to present a new method to calculate the dynamic stress intensity factors associated with the propagation of anti-plane kinked or branched cracks [9, 10]. This approach allows the exact calculation of the corresponding dynamic stress intensity factors. The latter are very important quantities in dynamic brittle fracture mechanics, since they determine the crack path and eventual branching instabilities. As an illustration, we consider the configuration depicted in Fig. 1 of an initially propagating antiplane crack that branches into two cracks that merge symmetrically. The explicit dependence of the stress intensity factor just after branching is given as a function of the stress intensity factor just before branching, the branching angle and the instantaneous velocity of the crack tip. The jump in the dynamic energy release rate due to the branching process is also computed. Similarly to the single crack case, a growth criterion for a branched crack is applied. It is based on the equality between the energy flux into each propagating tip and the surface energy which is added as a result of this propagation. It is shown that the minimum speed of the initial single crack which allows branching is equal to $0.39c$, where c is the shear wave speed. At the branching threshold, the corresponding bifurcated cracks start their propagation at a vanishing speed with a branching angle of approximately 40 degrees.

Using these exact results, the branching of a single propagating crack under mode I loading is also considered. It is shown that the formulation of the corresponding model problem is identical to the anti-plane case. The difficulty for solving completely the branching problem under plane loading configurations lies in the existence of two characteristic wave speeds and in the vectorial nature of the displacement field. However, this analogy allows the reasonable hypothesis that under plane loading configurations, the jump in the energy release rate due to branching is also maximized when the branches start to propagate quasi-statically. Using the Eshelby's approach, the branching of a single propagating crack under mode I loading is found to be energetically possible when its speed exceeds a threshold value. The critical branching parameters depend of the criterion applied for the selection of the paths followed by the bifurcated cracks. For instance, the maximum energy release rate criterion [11] or the principal of local symmetry [12]. It is found that the critical velocity for branching of the initial single crack is weakly sensitive to the applied criterion. However, the principal of local symmetry gives a larger branching angle, which is more consistent with experimental observations. Finally, it is shown that an increasing fracture energy with the velocity results in a decrease in the critical velocity at which branching is energetically possible.

References

- [1] Ravi-Chandar, K., Knauss, W.G.: An experimental investigation into dynamic fracture—III. On steady-state crack propagation and crack branching. *Int. J. Fracture* **26**:141–154, 1984.
- [2] Boudet, J.F., Ciliberto, S., Steinberg, V.: Dynamics of crack propagation in brittle materials. *J. Phys. II France* **6**:1493–1516, 1996.
- [3] Sharon, E., Fineberg, J.: Microbranching instability and the dynamic fracture of brittle materials. *Phys. Rev. B* **54**:7128–7139, 1996.
- [4] Eshelby, J.D.: Energy relations and the energy-momentum tensor in continuum mechanics. *Inelastic Behavior of Solids* (ed. Kanninen, M.F., Adler, W.F., Rosenfield, A.R. and Jaffee, R.I.), McGraw-Hill, New York, 77–115, 1970.
- [5] Rice, J.R., Ben-Zion, Y., Kim, K.S.: Three-dimensional perturbation solution for a dynamic planar crack moving unsteadily in a model elastic solid. *J. Mech. Phys. Solids* **42**:813–843, 1994.
- [6] Freund, L.B.: *Dynamic Fracture Mechanics*. Cambridge University Press, NY 1990.
- [7] Sharon, E., Fineberg, J.: Confirming the continuum theory of dynamic brittle fracture for fast cracks. *Nature* **399**:333–335, 1999.
- [8] Washabaugh, P.D., Knauss, W.G.: A reconciliation of dynamic crack velocity and Rayleigh wave speed in isotropic brittle solids. *Int. J. Fracture* **65**:97–114, 1994.
- [9] Adda-Bedia, M., Arias, R.: Brittle fracture dynamics with arbitrary paths—I. Dynamic crack kinking under general antiplane loading. *J. Mech. Phys. Solids* **51**:1287–1304, 2003.
- [10] Adda-Bedia, M.: Brittle fracture dynamics with arbitrary paths—II. Dynamic crack branching under general antiplane loading. *J. Mech. Phys. Solids* 2004.
- [11] Erdogan, G., Sih, G.C.: On the crack extension in plates under plane loading and transverse shear. *J. Basic Engng.* **85**:519–527, 1963.
- [12] Gol'dstein, R.V., Salganik, R.L.: Brittle fracture of solids with arbitrary cracks. *Int. J. Fracture* **10**:507–523, 1974.