

Nanobioremediation Technologies for Sustainable Environment

A. Sherry Davis, P. Prakash and K. Thamaraiselvi

Abstract Hybrid technologies like nanobioremediation are significant in transforming and detoxifying pollutants which harm the ecosystem. In situ or ex situ it has the potential for large scale clean-up activities with reduced cost and minimal harmful byproducts. Here five nanoscale metallic biosynthesized particles formed the topic of study. Zn, Ag, Au, Fe and Cu particles can be biosynthesized using plant extracts, bacteria, fungi and algae. The potential of these metallic nanoparticles to degrade and remedy various contaminants in the environment has been researched widely. A combination of biosynthesis and remediation lead to sustainable development and ultimately a sustained environment.

Keywords Biosynthesis · Nanoparticles · Bioremediation · Environment

1 Introduction

Environmental sustainability is defined as responsible interaction with the environment to avoid depletion or degradation of natural resources and allow for long term environmental quality. However the world's definition of sustainability is sustainable development which results in environmental degradation. The advancement in science and technology contribute directly or indirectly to the increase in waste and toxic materials in the environment. Environmental sustainability programs include protection and restoration of the natural environment.

A. Sherry Davis · P. Prakash · K. Thamaraiselvi (✉)
Molecular Bioremediation and Nano Biotechnology Laboratory,
Department of Environmental Biotechnology, School of Environmental Sciences,
Bharathidasan University, Tiruchirappalli, Tamil Nadu, India
e-mail: thamaraiselvi@gmail.com

One of the restoration strategies used nowadays is bioremediation which makes use of microorganisms. The advantages of bioremediation over conventional treatments is cost effectiveness, high competence, minimization of chemical and biological sludge, selectivity to specific metals, no supplementary nutrient requirements, regeneration of biosorbent, and the possibility of metal recovery (Kratochvil and Volesky 1998). However this treatment method is not feasible for sites contaminated with toxic substances as it is harmful to microorganisms.

Nanoparticles however have the unique capability to remediate such toxic environments and also provide a healthy substrate for microbial activity thus speeding up the process of environment clean-up. Nanoparticles can be prepared by physico-chemical methods (Masala and Seshadri 2004; Swihart 2003) but the use of hazardous chemicals, high cost and toxic byproducts has given biological nanoparticle synthesis an advantage (Konishi et al. 2006). Nanobioremediation is the use of nanoparticles to remove pollutants by enhancing microbial activity.

Nanoparticles (NPs) may be either metallic or nonmetallic and differently shaped. NPs are of the following types—single metal NPs, bimetallic NPs, carbon based NPs, modified NPs etc. Metal nanoparticles have applications in different fields like medical imaging (Lee et al. 2008a), drug delivery (Horcajada et al. 2008), electronics (Lipovsky et al. 2008), nanocomposites (Seager et al. 2007), biolabeling (Liang et al. 2006), biocide or antimicrobial agents (Sanpui et al. 2008), sensors (Jiang et al. 2008), non-linear optics (Ebothe et al. 2006), hyperthermia of tumors (Pissuwan et al. 2006), intercalation materials for electrical batteries (Klaus-Joerger et al. 2001), optical receptors (Dahan et al. 2003) etc. The wide range of applications of nanoparticles is due to their unique optical, thermal, electrical, chemical, and physical properties (Panigrahi et al. 2004).

Nanoscale materials has the following characteristics—Larger surface area per unit mass, show quantum effect and hence is more reactive, exhibit plasmon resonance and can diffuse or penetrate contaminated sites easily. Selective sample extraction can be achieved by modifying the surface functionality of the nanoparticles.

In this review we have focused on the biosynthesis of five nanoparticles (Zn, Ag, Au, Fe, Cu) using plant extracts, bacteria, fungi and algae. We have also compiled the different degrading and remediation activities of these nanoparticles for possible large scale restoration programs.

2 Biosynthesis of Zinc Nanoparticles (ZnNP's)

In the last two decades ZnNP's have been given significant attention owing to its applications in varied fields like piezoelectric films (Martin et al. 2000), piezoelectric sensor (Wang et al. 2004), ceramics (Grigorjeva et al. 2008), photo catalysis

Table 1 Biosynthesis of ZnNPs

Materials	Organism	References
Plant	<i>Aloe barbadensis miller</i>	Sangeetha et al. (2011)
	<i>Calotropis gigantea</i>	Vidya et al. (2013)
	<i>Coriandrum sativum</i> , <i>Acalypha indica</i>	Gnanasangeetha and Thambavani (2013a, b)
	<i>Parthenium hysterophorus</i>	Rajiv et al. (2013)
	<i>Azadirachta indica</i>	Gnanasangeetha and Thambavani (2013c)
Bacteria	<i>Lactobacillus</i>	Prasad and Jha (2009)
	<i>Lactobacillus plantarum</i>	Ameer et al. (2010)
	<i>Aeromonas hydrophila</i>	Jayaseelan et al. (2012)
Fungi	<i>Candida albicans</i>	Mashrai et al. (2013)
Algae	<i>Cystophora moniliformis</i>	Vigneshwaran et al. (2006)

(Pal and Sharon 2002) solar cells (Gordillo 2002), bio-imaging, drug delivery (Xiong 2013) actuator, biosensors (Yang et al. 2012) and water purification specifically arsenic removal (Singh et al. 2013b).

Owing to the wide applications of ZnNP's it has been synthesized by methods such as wet chemical method (Lee et al. 2009; Mehta et al. 2012), organic solvent method (Mezni et al. 2012) and microwave method (Nehru et al. 2012). However biological synthesis using bacteria, fungi, algae and plant extracts is the method of choice and many researchers have been successful in synthesizing ZnNPs (Table 1).

3 Biosynthesis of Silver Nanoparticles (AgNP's)

Nanobiotechnological developments have led to the development of environmentally benign nanoparticles. AgNP's have applications in non-linear optics, as intercalation materials for electrical batteries, optical receptors, as a catalyst and as an antibacterial. The antimicrobial activity of silver nanoparticles has many uses like the production of AgNP coated blood collecting vessels, coated capsules, bandaids etc. (Geoprincy et al. 2011). Biosynthesis of AgNP's using biological entities is tabulated in Table 2.

Table 2 Biosynthesis of AgNP's

Materials	Organism	References
Plant	<i>Euphorbia hirta</i> , <i>Nerium indicum</i>	Priya et al. (2011)
	<i>Cleome viscosa</i>	Yamini et al. (2011)
	<i>Trigonella foenumgraecum</i>	Singh et al. (2011)
	<i>Cycas</i>	Jha and Prasad (2010)
	<i>Ocimum</i>	Mallikarjuna et al. (2011)
	<i>Sinapis arvensis</i>	Khatami et al. (2015)
	<i>Iresine herbstii</i>	Dipankar and Murugan (2012)
	<i>Lantana camara</i>	Kumar et al. (2015)
	<i>Citrus limon</i>	Prathna et al. (2011)
	<i>Artemisia nilagirica</i>	Vijayakumar et al. (2013)
	<i>Pithophora oedogonia</i>	Sinha et al. (2015)
	<i>Butea monosperma</i>	Chaturvedi and Verma (2015)
	<i>Nerium oleander</i>	Subbaiya et al. (2014)
Bacteria	<i>Morganella psychrotolerans</i>	Ramanathan et al. (2010)
	<i>Bacillus licheniformis</i>	Kalimuthu et al. (2008)
	<i>Streptomyces sp. LK3</i>	Karthik et al. (2014)
	<i>Staphylococcus aureus</i>	Nanda and Saravanan (2009)
	<i>Brevibacterium casei</i>	Kalishwaralal et al. (2010)
	<i>Streptomyces rochei</i>	Selvakumar et al. (2012)
Fungi	<i>Aspergillus fumigates</i>	Bhainsa and D'souza (2006)
	<i>Aspergillus tamarii</i>	Kumar et al. (2012)
	<i>Schizophyllum commune</i> (mushroom fungus)	Arun et al. (2014)
	<i>Trichoderma reesei</i>	Vahabi et al. (2011)
	<i>Cladosporium cladosporioides</i>	Balaji et al. (2009)
	<i>Fusarium oxysporum</i>	Birla et al. (2013)
	<i>Aspergillus clavatus</i>	Verma et al. (2010a, b)
Algae	<i>Navicula atomus</i> , <i>Diadsmis gallica</i> , <i>Stauroneis sp.</i> <i>Sargassum wightii</i> , <i>Fucus vesiculosus</i>	Asmathunisha and Kathiresan (2013)
	<i>Turbinaria conoides</i>	Rajeshkumar et al. (2012)
	<i>Sargassum longifolium</i>	Devi et al. (2013)
	<i>Caulerpa racemosa</i>	Kathiraven et al. (2015)
	<i>Cystophora moniliformis</i>	Prasad et al. (2013)
	<i>Sargassum muticum</i>	Azizi et al. (2013)

4 Biosynthesis of Gold Nanoparticles (AuNP's)

Gold nanoparticles show high chemical reactivity on comparison with bulk gold. It exhibits surface plasmon oscillations which can be used in fields like labeling, imaging and sensing. AuNPs are biocompatible and hence can be used in disease diagnosis and therapy. AuNPs have been biosynthesized from plant extracts, bacteria, fungi and algae. Table 3 focuses on the biological synthesis of AuNP's.

Table 3 Biosynthesis of AuNP's

Materials	Organism	References
Plant	<i>Sorbus aucuparia</i>	Dubey et al. (2010)
	<i>Chenopodium album</i>	Dwivedi and Gopal (2010)
	<i>Maduca longifolia</i>	Fayaz et al. (2011)
	<i>Rosa hybrida</i>	Noruzi et al. (2011)
	<i>Ocimum sanctum</i>	Philip and Unni (2011)
	<i>Magnolia kobus</i> , <i>Diopyros kaki</i>	Song et al. (2009)
	<i>Sesbania drummondii</i>	Sharma et al. (2007)
Bacteria	<i>Rhodopseudomonas capsulate</i>	He et al. (2007)
	<i>Escherichia coli DH5a</i>	Du et al. (2007)
	<i>Thermomonospora sp.</i>	Kasthuri et al. (2009)
	<i>Rhodococcus sp.</i>	Park et al. (2011)
	<i>Delftia acidovorans</i>	Johnston et al. (2013)
	<i>Pseudomonas aeruginosa</i>	Narayanan and Sakthivel (2010)
	<i>Geobacillus sp. strain ID17</i>	Correa-Llantén et al. (2013)
	<i>Klebsiella pneumonia</i>	Malarkodi et al. (2013)
Fungi	<i>Marinobacter pelagius</i>	Sharma et al. (2012)
	<i>Candida albicans</i>	Chauhan et al. (2011)
	<i>Fusarium semitectum</i>	Sawle et al. (2016)
	<i>Epicoccum nigrum</i>	Sheikhloo et al. (2011)
	<i>Cylindrocladium floridanum</i>	Narayanan and Sakthivel (2011)
	<i>Aspergillus clavatus</i>	Verma et al. (2010a, b)
	<i>Neurospora crassa</i>	Castro-Longoria et al. (2011)
	<i>Aspergillus oryzae</i>	Binupriya et al. (2010)
	<i>Hormoconis resinae</i>	Mishra et al. (2010)
	<i>Penicillium brevicompactum</i>	Mishra et al. (2011)
Algae	<i>Saccharomyces cerevisiae</i>	Sen et al. (2011)
	<i>Sargassum wightii</i>	Singaravelu et al. (2007)
	<i>Shewanella oneidensis</i>	Suresh et al. (2011)
	<i>laminaria japonica</i>	Ghodake and Lee (2011)
	<i>tetraselmis kochinensis</i>	Senapati et al. (2012)
	<i>Klebsormidium flaccidum</i>	Dahoumane et al. (2012)
	<i>Centella asiatica</i>	Das et al. (2010)
	<i>Lemanea fluviatilis</i>	Sharma et al. (2014)
	<i>Sargassum muticum</i>	Namvar et al. (2015)
	<i>Padina gymnospora</i>	Singh et al. (2013a)

5 Synthesis of Iron Nanoparticles (FeNP's)

The three major forms of iron oxides found in nature are magnetite (Fe_3O_4), maghemite ($\gamma\text{-Fe}_2\text{O}_3$), and hematite ($\alpha\text{-Fe}_2\text{O}_3$) (Cornel and Schwertmann 1996). Of all the different kinds of iron oxides, magnetite have aroused the interest of many researchers owing to the fact that it can be easily synthesised, can be modified or coated and has superparamagnetic characteristics (McHenry and Laughlin 2000). This property makes it easy to separate these supermagnetic particles from aqueous solution and complicated matrices by applying an external magnetic field. Some problems associated with using FeNP's are its intrinsic instability resulting in the formation of agglomerates and its high chemical activity which promotes oxidation, subsequent loss of magnetism and dispersion. Hence for application in various fields these nanoparticles have to be coated with either inorganic substances like silica, carbon etc., or with organic species like surfactants and polymers (Wu et al. 2013). Iron nanoparticles have been synthesized by various chemical and physical methods (Afonso et al. 2011). Some emerging methods of synthesis of iron nanoparticles are the use of microorganisms and plant extracts which exclude the use of harmful chemicals and toxic byproducts (Table 4).

Table 4 Biosynthesis of FeNP's

Materials	Organism	References
Plant	<i>Sorghum sp.</i>	Njagi et al. (2010)
	<i>Green tea</i>	Shahwan et al. (2011)
	<i>Musa paradisiaca</i>	Herlekar et al. (2014)
	<i>Dodonaea viscosa</i>	Daniel et al. (2013)
	<i>Musa paradisiaca</i>	Venkateswarlu et al. (2013)
	<i>Terminalia chebula</i>	Kumar et al. (2013)
	<i>Eucalyptus tereticornis</i> , <i>Melaleuca nesophila</i> , and <i>Rosemarinus officinalis</i>	Wang et al. (2014)
	<i>Aloe vera</i>	Phumying et al. (2013)
Bacteria	<i>Bacillus subtilis</i>	Sundaram et al. (2012)
	<i>Shewanella oneidensis</i>	Perez-Gonzalez et al. (2010)
	<i>E. coli</i>	Lee et al. (2008a, b)
	<i>Klebsiella oxytoca</i>	Arçon et al. (2012)
Fungi	<i>Fusarium oxysporum</i>	Bharde et al. (2006)
	<i>C. globosum</i>	Kaul et al. (2012)
	<i>Plerotus Sp.</i>	Mazumdar and Haloi (2011)
	<i>Alternaria alternata</i>	Mohamed et al. (2015)
Algae	<i>Sargassum muticum</i>	Mahdavi et al. (2013)
	<i>Sargassum myriocystem</i>	Sangeetha and Kumaraguru (2014)

6 Synthesis of Copper Nanoparticles (CuNP's)

Copper is one of the most widely used materials in the world owing to its usage in fields like electricity, optics, catalysis, biomedical and antimicrobial applications. Many researchers have been successful in the biosynthesis of copper nanoparticles using the seed, flower, leaves and fruit skin of plants (Table 5). The nanoparticles synthesized from plant extracts were found to be covered by the medicinal properties of the plant. CuNP is an antimicrobial agent used in food packaging and water treatment.

Table 5 Biosynthesis of CuNP's

Materials	Organism	References
Plant	<i>Magnolia kobus</i>	Lee et al. (2013)
	<i>Pterocarpus marsupium</i>	Sharma et al. (2015a)
	<i>Malva sylvestris</i>	Awwad et al. (2015)
	<i>Calotropis gigantea</i>	Sharma et al. (2015b)
	<i>Tamarix gallica</i>	Nasrollahzadeh et al. (2015)
	<i>Aloe barbadensis miller</i>	Kumar et al. (2015)
	<i>Tabernaemontana divaricate</i>	Sivaraj et al. (2014a, b)
	<i>Pyrus pyrifolia</i>	Sundaramurthy and Parthiban (2015)
	<i>Acalypha indica</i>	Sivaraj et al. (2014b)
	<i>Nerium oleander</i>	Gopinath et al. (2014)
	<i>Tridax procubens</i>	Gopalakrishnan et al. (2012)
	<i>Calotropis procera L</i>	Harne et al. (2012)
Bacteria	<i>M. psychrotolerans</i> and <i>M. organii</i> RP42	Ramanathan et al. (2011)
	<i>Pseudomonas stutzeri</i>	Varshney et al. (2010)
	<i>Pseudomonas fluorescens</i>	Shantkriti and Rani (2014)
	<i>Serratia</i>	Saif Hasan et al. (2008)
	<i>Streptomyces sp.</i>	Usha et al. (2010)
	<i>Escherichia coli</i>	Singh et al. (2010)
Fungi	<i>Hypocrea lixii</i>	Salvadori et al. (2013)
	<i>Penicillium aurantiogriseum</i> , <i>Penicillium citrinum</i> , <i>Penicillium waksmanii</i>	Honary et al. (2012)
	<i>Aspergillus Sp.</i>	Cuevas et al. (2015)
Algae	<i>Bifurcaria bifurcata</i>	Abboud et al. (2014)

7 Nano Bioremediation

Population growth, rapid industrialization and long term droughts has resulted in the spread of wide range of pollutants in surface and ground water system (Chong et al. 2010). The major contaminants include heavy metals, inorganic compounds, organic pollutants and many other complex compounds (Li et al. 2011). It is imperative to remove these toxic substances as they are harmful not only to human beings but also to the ecological environment (Pang et al. 2011). Waste water treatment processes like photo catalytic oxidation, adsorption/separation processing and bioremediation (Huang et al. 2006; Zelmanov and Semiat 2008) have been tried and tested. But factors like efficiency, operational method, energy requirements and high cost have restricted their usability (Huang et al. 2006; Zelmanov and Semiat 2008). In the past two decades nano scale materials have been used as an alternative to existing treatment materials due to its efficiency, cost effectiveness and eco-friendly nature (Dastjerdi and Montazer 2010).

Iron NPs is considered to be the first nanoparticle to be used in environmental clean-up (Tratnyek and Johnson 2006). Current applications of iron-based technologies in contaminated land or groundwater remediation can be broadly divided into two groups, based on the chemistry involved in the remediation process: technologies which use iron as a sorbent (adsorptive/immobilization technologies) and as an electron donor to break down or to convert contaminants into a less toxic or mobile form (reductive technologies) (Cundy et al. 2008). However, it should be noted that many technologies utilize both these processes.

Zn NPs a semiconductor photo catalyst have been extensively studied by researchers around the globe owing to its capacity to degrade organic dyes. ZnNPs can photo catalyse and cause the complete degradation of a wide variety of compounds from dyes to phenols and pharmaceutical drugs (El-Kemary et al. 2010).

Among all nanoparticles noble metal nanoparticles like gold and silver have enormous applications in diverse areas. In recent times researchers have analyzed the potential of Au and Ag nanoparticles in the degradation of organic dyes. Copper nanoparticles also can be used in the degradation of organic dyes with good results. Table 6 focusses on the degradation and subsequent remediation of various environmental pollutants.

Table 6 Remediation by metal nanoparticles

Metal nanoparticles	Remediation	References
Iron	Pentachlorophenol	Kim and Carraway (2000)
	Chlorobenzene	Lee et al. (2011)
	Dissolved sulfides	Chaung et al. (2014)
	Pyrene	Chang and Kang (2009)
	Dibenzo- <i>p</i> -dioxins and furans	Kim et al. (2008)
	Nitrate	Ryu et al. (2011)
	RDX (hexahydro-1,3,5-trinitro-1,3,5-triazine)	Naja et al. (2008)
	Cationic and anionic dyes	Shahwan et al. (2011)
	Alachlor, pretilachlor	Kim et al. (2006)
	Perchlorate	Moore et al. (2003)
	Brominated methanes	Lim et al. (2007)
	Chlorinated ethanes	Song and Carraway (2005)
	4,4'- dinitrostilbene-2,2'-disulfonic acid	Fan et al. (2007)
	Uranium	Fan et al. (2012)
	Lindane, atrazine	Joo and Zhao (2008)
	Alachlor and atrazine	Bezbaruah et al. (2009)
	Polychlorinated biphenyls (PCBs)	Choi et al. (2008)
	Atrazine	Satapanajaru et al. (2008)
	Cr(VI)	Cutting et al. (2010)
	Ni(II)	Li and Zhang (2006)
	As(V), Cr(VI)	Pradeep (2009)
	Cu(II), Pb(II)	Mahdavian and Mirrahimi (2010)
	Pb(II), Hg(II)	Ambashta and Sillanpää (2010)
	Cu(II), Cr(VI)	Huang and Chen (2009)
	Cr(VI) and Cd(II)	Li et al. (2013)
	Trichloro ethylene	Smuleac et al. (2011)
	Cd ²⁺	Boparai et al. (2013)
	Metalachlor	Santornchot et al. (2010)
	Dichloroethane	Wei et al. (2012)

(continued)

Table 6 (continued)

Metal nanoparticles	Remediation	References
Zinc	4-chloro catechol	Kamat (2002)
	Cd(II)	Srivastava et al. (2013)
	Brown CGG dye	Islam (2015)
	Methylene blue	Srivastava et al. (2013)
	RhodamineB	Ali et al. (2013)
	Organic dyes	Sanna et al. (2016)
	Direct red 23	Kumar et al. (2014)
	Eriochrome black-T dye	Kazeminezhad and Sadollahkhani (2014)
	Methylene blue	Jain et al. (2014)
	Formaldehyde	Darvishi Cheshmeh Soltani et al. (2015)
	Phenol	Kruefu et al. (2012)
	Congo Red and Benzopurpurine 4B	Elaziouti and Ahmed (2011)
	Malachite green	Khezami et al. (2016)
	Resorcinol	Pardeshi and Patil (2009)
	Rhodamine B	Zhao and Wang (2011)
	fuchsine	Zhou et al. (2009)
Gold	Methylene blue	Suvith and Philip (2014)
	Tertiary dye effluent (Methyl orange, Acid red 88, Acid orange 10)	Sathishkumar et al. (2013)
	4-nitrophenol	Huang et al. (2009)
	Methylene blue	Gupta et al. (2010)
Copper	Methylene blue	Sinha and Ahmaruzzaman (2015)
	Methyl orange	Soomro and Nafady (2015)
	Dichloromethane	Huang et al. (2012)
Silver	Organic dyes (methyl violet, saffranin, eosin methylene blue, methyl orange)	Bhakya et al. (2015)
	Methylene blue	Morones et al. (2005)
	4-nitrophenol	Gangula et al. (2011)
	Congored	Modi et al. (2015)
	Coomassie Brilliant Blue G-250	Arunachalam et al. (2012)
	Textile Effluent	Corso and Almeida (2009)

8 Conclusions

Nanotechnology is revolutionizing the way we live. The unique characteristics of nanoparticles have made them the particle of choice in many fields including remediation of environmental pollutants. Ecofriendly synthesis of nanoparticles coupled with remediation can go a long way in promoting sustainability. Biosynthesis helps minimize the use of harmful chemicals and solvents and is simple, cost effective and time saving. Zn, Ag, Au, Fe and Cu nanoparticles have been synthesized by many researchers using various biological methods. Although there are many studies on the synthesis of Au, Ag, Cu and Zn nanoparticles, very few have concentrated on the biosynthesis of FeNPs using bacteria, fungi and algae. Green synthesis of metal NPs using plant extract seems to be the subject of choice of a majority of researchers, however only a few is documented in this review. On comparing the bioremediation properties of these NPs it was noted that FeNPs has a wider application, degrading pollutants like pesticides, dyes, hydrocarbons, TCE etc. Most of the other NPs find applications in the photocatalytic degradation of dyes. Considering the wide applications of FeNPs in remediation it is necessary to find novel methods to biosynthesize FeNPs on a large scale.

References

- Abboud Y, Saffaj T, Chagraoui A, El Bouari A, Brouzi K, Tanane O, Ihssane B (2014) Biosynthesis, characterization and antimicrobial activity of copper oxide nanoparticles (CONPs) produced using brown alga extract (*Bifurcaria bifurcata*). *App Nanosci* 4 (5):571–576
- Afonso MV, Bioucas-Dias JM, Figueiredo MA (2011) An augmented Lagrangian approach to the constrained optimization formulation of imaging inverse problems. *IEEE Trans Image Process* 20(3):681–695
- Ali MA, Idris MR, Quayum ME (2013) Fabrication of ZnO nanoparticles by solution-combustion method for the photocatalytic degradation of organic dye. *J Nanostruct Chem* 3(1):1–6
- Ambashta RD, Sillanpää M (2010) Water purification using magnetic assistance: a review. *J Hazard Mater* 180(1):38–49
- Ameer A, Faheem A, Nishat A, Chaman M, Naqvi AH (2010) Biosynthesis and characterization of ZnO nanoparticles using (*Lactobacillus plantarum*). *J Alloys Compd* 496:399–402
- Arçon I, Piccolo O, Paganelli S, Baldi F (2012) XAS analysis of a nanostructured iron polysaccharide produced anaerobically by a strain of *Klebsiella oxytoca*. *Biometals* 25(5): 875–881
- Arun G, Eyini M, Gunasekaran P (2014) Green synthesis of silver nanoparticles using the mushroom fungus *Schizophyllum commune* and its biomedical applications. *Biotechnol Bioprocess Eng* 19(6):1083–1090
- Arunachalam R, Dhanasingh S, Kalimuthu B, Uthirappan M, Rose C, Mandal AB (2012) Phytosynthesis of silver nanoparticles using *Coccinia grandis* leaf extract and its application in the photocatalytic degradation. *Colloids Surf B* 94:226–230
- Asmathunisha N, Kathiresan K (2013) A review on biosynthesis of nanoparticles by marine organisms. *Colloids Surf B* 103:283–287

- Awad AM, Albiss BA, Salem NM (2015) Antibacterial activity of synthesized copper oxide nanoparticles using *Malva sylvestris* leaf extract. *SMU Med J* 2:91–101
- Azizi S, Namvar F, Mahdavi M, Ahmad MB, Mohamad R (2013) Biosynthesis of silver nanoparticles using brown marine macroalga *Sargassum muticum* aqueous extract. *Materials* 6 (12):5942–5950
- Balaji DS, Basavaraja S, Deshpande R, Mahesh DB, Prabhakar BK, Venkataraman A (2009) Extracellular biosynthesis of functionalized silver nanoparticles by strains of *Cladosporium cladosporioides* fungus. *Colloids Surf B* 68(1):88–92
- Bezbaruah AN, Thompson JM, Chisholm BJ (2009) Remediation of alachlor and atrazine contaminated water with zero-valent iron nanoparticles. *J Environ Sci Health, Part B* 44 (6):518–524
- Bhainsa KC, D'souza SF (2006) Extracellular biosynthesis of silver nanoparticles using the fungus *Aspergillus fumigatus*. *Colloids Surf B* 47(2):160–164
- Bhakya S, Muthukrishnan S, Sukumaran M, Muthukumar M, Kumar S, Rao MV (2015) Catalytic degradation of organic dyes using synthesized silver nanoparticles: a green approach. *J Bioremediat Biodegrad*
- Bharde A, Rautaray D, Bansal V, Ahmad A, Sarkar I, Yusuf SM, Sastry M (2006) Extracellular biosynthesis of magnetite using fungi. *Small* 2(1):135–141
- Binupriya AR, Sathishkumar M, Vijayaraghavan K, Yun SI (2010) Bioreduction of trivalent aurum to nano-crystalline gold particles by active and inactive cells and cell-free extract of *Aspergillus oryzae* var. *viridis*. *J Hazard Mater* 177(1):539–545
- Birla SS, Gaikwad SC, Gade AK, Rai MK (2013) Rapid synthesis of silver nanoparticles from *Fusarium oxysporum* by optimizing physiocultural conditions. *Scientific World J.* <http://dx.doi.org/10.1155/2013/796018>
- Boparai HK, Joseph M, O'Carroll DM (2013) Cadmium (Cd²⁺) removal by nano zerovalent iron: surface analysis, effects of solution chemistry and surface complexation modeling. *Environ Sci Pollut Res* 20(9):6210–6221
- Castro-Longoria E, Vilchis-Nestor AR, Avalos-Borja M (2011) Biosynthesis of silver, gold and bimetallic nanoparticles using the filamentous fungus *Neurospora crassa*. *Colloids Surf B* 83 (1):42–48
- Chang MC, Kang HY (2009) Remediation of pyrene-contaminated soil by synthesized nanoscale zero-valent iron particles. *J Environ Sci Health, Part A* 44(6):576–582
- Chaturvedi V, Verma P (2015) Fabrication of silver nanoparticles from leaf extract of *Butea monosperma* (Flame of Forest) and their inhibitory effect on bloom-forming cyanobacteria. *Bioresour Bioprocess* 2(1):18
- Chauhan A, Zubair S, Tufail S, Sherwani A, Sajid M, Raman SC, Owais M (2011) Fungus-mediated biological synthesis of gold nanoparticles: potential in detection of liver cancer. *Int J Nanomed* 6:2305–2319
- Chuang SH, Wu PF, Kao YL, Yan W, Lien HL (2014) Nanoscale zero-valent iron for sulfide removal from digested piggery wastewater. *J Nanomater*
- Choi H, Al-Abed SR, Agarwal S, Dionysiou DD (2008) Synthesis of reactive nano-Fe/Pd bimetallic system-impregnated activated carbon for the simultaneous adsorption and dechlorination of PCBs. *Chem Mater* 20(11):3649–3655
- Chong MN, Jin B, Chow CW, Saint C (2010) Recent developments in photocatalytic water treatment technology: a review. *Water Res* 44(10):2997–3027
- Cornell RM, Schwertmann U (1996) Structure, properties, reactions, occurrence and uses. In: *The iron oxides*. VCH, Weinheim, pp 375–395
- Correa-Llantén DN, Muñoz-Ibacache SA, Castro ME, Muñoz PA, Blamey JM (2013) Gold nanoparticles synthesized by *Geobacillus* sp. strain ID17 a thermophilic bacterium isolated from Deception Island, Antarctica. *Microb Cell Fact* 12(1):1
- Corso CR, De Almeida ACM (2009) Bioremediation of dyes in textile effluents by *Aspergillus oryzae*. *Microb Ecol* 57(2):384–390

- Cuevas R, Durán N, Diez MC, Tortella GR, Rubilar O (2015) Extracellular biosynthesis of copper and copper oxide nanoparticles by *Stereum hirsutum*, a native white-rot fungus from Chilean forests. *J Nanomater* 57
- Cundy AB, Hopkinson L, Whitby RL (2008) Use of iron-based technologies in contaminated land and groundwater remediation: a review. *Sci Total Environ* 400(1):42–51
- Cutting RS, Coker VS, Telling ND, Kimber RL, Pearce CI, Ellis BL, Arenholz E (2010) Optimizing Cr (VI) and Tc (VII) remediation through nanoscale biomineral engineering. *Environ Sci Technol* 44(7):2577–2584
- Dahan M, Levi S, Luccardini C, Rostaing P, Riveau B, Triller A (2003) Diffusion dynamics of glycine receptors revealed by single-quantum dot tracking. *Science* 302(5644):442–445
- Dahoumane SA, Djediat C, Yéprémian C, Couté A, Fiévet F, Coradin T, Brayner R (2012) Recycling and adaptation of *Klebsormidium flaccidum* microalgae for the sustained production of gold nanoparticles. *Biotechnol Bioeng* 109(1):284–288
- Daniel SK, Vinothini G, Subramanian N, Nehru K, Sivakumar M (2013) Biosynthesis of Cu, ZVI, and Ag nanoparticles using *Dodonaea viscosa* extract for antibacterial activity against human pathogens. *J Nanopart Res* 15(1):1–10
- Darvishi Cheshmeh Soltani R, Rezaee A, Safari M, Khataee AR, Karimi B (2015) Photocatalytic degradation of formaldehyde in aqueous solution using ZnO nanoparticles immobilized on glass plates. *Desalin Water Treat* 53(6):1613–1620
- Das RK, Borthakur BB, Bora U (2010) Green synthesis of gold nanoparticles using ethanolic leaf extract of *Centella asiatica*. *Mater Lett* 64(13):1445–1447
- Dastjerdi R, Montazer M (2010) A review on the application of inorganic nano-structured materials in the modification of textiles: focus on anti-microbial properties. *Colloids Surf B* 79(1):5–18
- Devi JS, Bhimba BV, Peter DM (2013) Production of biogenic silver nanoparticles using *Sargassum longifolium* and its applications. *Indian J. Mar Sci* 42(1):125–130
- Dipankar C, Murugan S (2012) The green synthesis, characterization and evaluation of the biological activities of silver nanoparticles synthesized from *Iresine herbstii* leaf aqueous extracts. *Colloids Surf B*, 98:112–119
- Du L, Jiang H, Liu X, Wang E (2007) Biosynthesis of gold nanoparticles assisted by *Escherichia coli* DH5 α and its application on direct electrochemistry of hemoglobin. *Electrochem Commun* 9(5):1165–1170
- Dubey SP, Lahtinen M, Särkkä H, Sillanpää M (2010) Bioprospective of *Sorbus aucuparia* leaf extract in development of silver and gold nanocolloids. *Colloids Surf B* 80(1):26–33
- Dwivedi AD, Gopal K (2010) Biosynthesis of silver and gold nanoparticles using *Chenopodium album* leaf extract. *Colloids Surf A* 369(1):27–33
- Ebothe J, Kityk IV, Benet S, Claudet B, Plucinski KJ, Ozga K (2006) Photoinduced effects in ZnO films deposited on MgO substrates. *Opt Commun* 268(2):269–272
- Elaziouti A, Ahmed B (2011) ZnO-assisted photocatalytic degradation of Congo Red and benzopurpurine 4B in aqueous solution. *J Chem Eng Process Technol* 2:1–9
- El-Kemary M, El-Shamy H, El-Mehasseb I (2010) Photocatalytic degradation of ciprofloxacin drug in water using ZnO nanoparticles. *J Lumin* 130(12):2327–2331
- Fan X, Zhang F, Zhang G, Du J (2007) Mechanism of 5-amino-2-formylbenzene sulfonic acid formation during reduction of 4, 4'-dinitrostilbene-2, 2'-disulfonic acid by Zero-Valent iron. *Dyes Pigm* 75(1):189–193
- Fan FL, Qin Z, Bai J, Rong WD, Fan FY, Tian W, Zhao L (2012) Rapid removal of uranium from aqueous solutions using magnetic Fe₃O₄@ SiO₂ composite particles. *J Environ Radioact* 106:40–46
- Fayaz AM, Girilal M, Venkatesan R, Kalaichelvan PT (2011) Biosynthesis of anisotropic gold nanoparticles using *Maduca longifolia* extract and their potential in infrared absorption. *Colloids Surf B* 88(1):287–291
- Gangula A, Podila R, Karanam L, Janardhana C, Rao AM (2011) Catalytic reduction of 4-nitrophenol using biogenic gold and silver nanoparticles derived from *Breynia rhamnoides*. *Langmuir* 27(24):15268–15274

- Geoprincy G, Saravanan P, Gandhi NN, Renganathan S (2011) A novel approach for studying the combined antimicrobial effects of silver nanoparticles and antibiotics through agar over layer method and disk diffusion method. *Dig J Nanomater Biostruct* 6(4):1557–1565
- Ghodake G, Lee DS (2011) Biological synthesis of gold nanoparticles using the aqueous extract of the brown algae *Laminaria japonica*. *J Nanoelectron Optoe* 6(3):268–271
- Gnanasangeetha D, Thambavani DS (2013a) One pot synthesis of zinc oxide nanoparticles via chemical and green method. *Research J Mater Sci*. ISSN, 2320:6055
- Gnanasangeetha D, Thambavani DS (2013b) Biogenic production of zinc oxide nanoparticles using *Acalypha indica*. *J Chem Bio Phy Sci* 4(1):238
- Gnanasangeetha D, Thambavani S (2013c). ZnO nanoparticle entrenched on activated silica as a proficient adsorbent for removal of As³⁺. *Int J Res Pharma Biomed Sci* 4(4):1295–1304
- Gopalakrishnan K, Ramesh C, Ragunathan V, Thamilselvan M (2012) Antibacterial activity of Cu₂O nanoparticles on *E. coli* synthesized from *Tridax procumbens* leaf extract and surface coating with polyaniline. *Dig J Nanomater Biostruct* 7(2):833–839
- Gopinath M, Subbaiya R, Selvam MM, Suresh D (2014) Synthesis of copper nanoparticles from *Nerium oleander* leaf aqueous extract and its antibacterial activity. *Int J Curr Microbiol App Sci* 3(9):814–818
- Gordillo G (2002) New materials used as optical window in thin film solar cells. *Surf Rev Lett* 9:1675–1680
- Grigorjeva L, Miller D, Grabis J, Monty C, Kalinko A, Smits K, Lojkowski W (2008) Luminescence properties of ZnO nanocrystals and ceramics. *IEEE Trans Nucl Sci* 55(3): 1551–1555
- Gupta N, Singh HP, Sharma RK (2010) Single-pot synthesis: plant mediated gold nanoparticles catalyzed reduction of methylene blue in presence of stannous chloride. *Colloids Surf A* 367 (1):102–107
- Harne S, Sharma A, Dhaygude M, Joglekar S, Kodam K, Hudlikar M (2012) Novel route for rapid biosynthesis of copper nanoparticles using aqueous extract of *Calotropis procera* L. latex and their cytotoxicity on tumor cells. *Colloids Surf B* 95:284–288
- He S, Guo Z, Zhang Y, Zhang S, Wang J, Gu N (2007) Biosynthesis of gold nanoparticles using the bacteria *Rhodopseudomonas capsulata*. *Mater Lett* 61(18):3984–3987
- Herlekar M, Barve S, Kumar R (2014) Plant-mediated green synthesis of iron nanoparticles. *J Nanopart*
- Honary S, Barabadi H, Gharaei-Fathabad E, Naghibi F (2012) Green synthesis of copper oxide nanoparticles using *Penicillium aurantiogriseum*, *Penicillium citrinum* and *Penicillium waksmanii*. *Dig J Nanomater Bios* 7:999–1005
- Horcajada P, Serre C, Maurin G, Ramsahye NA, Balas F, Vallet-Regi M, Férey G (2008) Flexible porous metal-organic frameworks for a controlled drug delivery. *J Am Chem Soc* 130 (21):6774–6780
- Huang SH, Chen DH (2009) Rapid removal of heavy metal cations and anions from aqueous solutions by an amino-functionalized magnetic nano-adsorbent. *J Hazard Mater* 163(1): 174–179
- Huang X, El-Sayed IH, Qian W, El-Sayed MA (2006) Cancer cell imaging and photothermal therapy in the near-infrared region by using gold nanorods. *J Am Chem Soc* 128(6):2115–2120
- Huang J, Wang W, Lin L, Li Q, Lin W, Li M, Mann S (2009) A general strategy for the biosynthesis of gold nanoparticles by traditional Chinese medicines and their potential application as catalysts. *Chem Asian J* 4(7):1050–1054
- Huang CC, Lo SL, Lien HL (2012) Zero-valent copper nanoparticles for effective dechlorination of dichloromethane using sodium borohydride as a reductant. *Chem Eng J* 203:95–100
- Islam AA, Ferdous T, Das AK (2015) Photodegradation of brown CGG dye using ZnO nanoparticles synthesized by ionic template method
- Jain N, Bhargava A, Panwar J (2014) Enhanced photocatalytic degradation of methylene blue using biologically synthesized “protein-capped” ZnO nanoparticles. *Chem Eng J* 243:549–555

- Jayaseelan C, Rahuman AA, Kirthi AV, Marimuthu S, Santhoshkumar T, Bagavan A, Rao KB (2012) Novel microbial route to synthesize ZnO nanoparticles using *Aeromonas hydrophila* and their activity against pathogenic bacteria and fungi. *Spectrochim Acta, Part A* 90:78–84
- Jha AK, Prasad K (2010) Green synthesis of silver nanoparticles using *Cycas leaf*. *J Green Nanotechno Phys Chem* 1(2):P110–P117
- Jiang G, Zhao D, Zhang G (2008) Seismic evidence for a metastable olivine wedge in the subducting Pacific slab under Japan Sea. *Earth Planet Sci Lett* 270(3):300–307
- Johnston CW, Wyatt MA, Li X, Ibrahim A, Shuster J, Southam G, Magarvey NA (2013) Gold biomineralization by a metallophore from a gold-associated microbe. *Nat Chem Biol* 9(4):241–243
- Joo SH, Zhao D (2008) Destruction of lindane and atrazine using stabilized iron nanoparticles under aerobic and anaerobic conditions: effects of catalyst and stabilizer. *Chemosphere* 70(3):418–425
- Kalimuthu K, Babu RS, Venkataraman D, Bilal M, Gurunathan S (2008) Biosynthesis of silver nanocrystals by *Bacillus licheniformis*. *Colloids Surf B* 65(1):150–153
- Kalishwaralal K, Deepak V, Pandian SRK, Kottaisamy M, BarathManiKanth S, Kartikeyan B, Gurunathan S (2010) Biosynthesis of silver and gold nanoparticles using *Brevibacterium casei*. *Colloids Surf B* 77(2):257–262
- Kamat PV (2002) Photophysical, photochemical and photocatalytic aspects of metal nanoparticles. *J Phys Chem* 106(32):7729–7744
- Karthik L, Kumar G, Kirthi AV, Rahuman AA, Rao KB (2014) *Streptomyces sp.* LK3 mediated synthesis of silver nanoparticles and its biomedical application. *Bioprocess Biosyst Eng* 37(2):261–267
- Kasthuri J, Kathiravan K, Rajendiran N (2009) Phyllanthin-assisted biosynthesis of silver and gold nanoparticles: a novel biological approach. *J Nanopart Res* 11(5):1075–1085
- Kathiraven T, Sundaramanickam A, Shanmugam N, Balasubramanian T (2015) Green synthesis of silver nanoparticles using marine algae *Caulerpa racemosa* and their antibacterial activity against some human pathogens. *Appl Nanosci* 5(4):499–504
- Kaul R, Kumar P, Burman U, Joshi P, Agrawal A, Raliya R, Tarafdar J (2012) Magnesium and iron nanoparticles production using microorganisms and various salts. *Mater Sci-Poland* 30(3):254–258
- Kazeminezhad I, Sadollahkhani A (2014) Photocatalytic degradation of Eriochrome black-T dye using ZnO nanoparticles. *Mater Lett* 120:267–270
- Khatami M, Pourseyedi S, Khatami M, Hamidi H, Zaeifi M, Soltani L (2015) Synthesis of silver nanoparticles using seed exudates of *Sinapis arvensis* as a novel bioresource, and evaluation of their antifungal activity. *Bioresour Bioprocess* 2(1):1
- Khezami L, Taha KK, Ghiloufi I, El Mir L (2016) Adsorption and photocatalytic degradation of malachite green by vanadium doped zinc oxide nanoparticles. *Water Sci Technol* 73(4):881–889
- Kim YH, Carraway ER (2000) Dechlorination of pentachlorophenol by zero valent iron and modified zero valent irons. *Environ Sci Technol* 34(10):2014–2017
- Kim HY, Kim IK, Shim JH, Kim YC, Han TH, Chung KC, Kim IS (2006) Removal of alachlor and pretilachlor by laboratory-synthesized zerovalent iron in pesticide formulation solution. *Bull Environ Contam Toxicol* 77:826
- Kim JH, Tratnyek PG, Chang YS (2008) Rapid dechlorination of polychlorinated dibenzo-p-dioxins by bimetallic and nanosized zerovalent iron. *Environ Sci Technol* 42(11):4106–4112
- Klaus-Joerges T, Joerges R, Olsson E, Granqvist CG (2001) Bacteria as workers in the living factory: metal-accumulating bacteria and their potential for materials science. *Trends Biotechnol* 19(1):15–20
- Konishi Y, Ohno K, Saitoh N, Nomura T, Nagamine S (2006) Microbial synthesis of noble metal nanoparticles using metal-reducing bacteria. In: *MRS proceedings*, vol. 942. Cambridge University Press, pp 0942-W13

- Kratochvil D, Volesky B (1998) Advances in the biosorption of heavy metals. *Trends Biotechnol* 16(7):291–300
- Kruefu V, Ninsonti H, Wetchakun N, Inceesungvorn B, Pookmanee P, Phanichphant S (2012) Photocatalytic degradation of phenol using Nb-loaded ZnO nanoparticles. *Eng J-CANDA* 16 (3):91–100
- Kumar RR, Priyadarsani KP, Thamaraiselvi K (2012) Mycogenic synthesis of silver nanoparticles by the Japanese environmental isolate *Aspergillus tamarii*. *J Nanopart Res* 14(5): 1–7
- Kumar KM, Mandal BK, Kumar KS, Reddy PS, Sreedhar B (2013) Biobased green method to synthesise palladium and iron nanoparticles using *Terminalia chebula* aqueous extract. *Spectrochim Acta, Part A* 102:128–133
- Kumar G, Kumar R, Hwang SW, Umar A (2014) Photocatalytic degradation of direct red-23 dye with ZnO nanoparticles. *J Nanosci Nanotechnol* 14(9):7161–7166
- Kumar PV, Shameem U, Kollu P, Kalyani RL, Pammi SVN (2015) Green synthesis of copper oxide nanoparticles using aloe vera leaf extract and its antibacterial activity against fish bacterial pathogens. *BioNanoScience* 5(3):135–139
- Lee HY, Li Z, Chen K, Hsu AR, Xu C, Xie J, Chen X (2008a) PET/MRI dual-modality tumor imaging using arginine-glycine-aspartic (RGD)-conjugated radiolabeled iron oxide nanoparticles. *J Nucl Med* 49(8):1371–1379
- Lee C, Kim JY, Lee WI, Nelson KL, Yoon J, Sedlak DL (2008b) Bactericidal effect of zero-valent iron nanoparticles on *Escherichia coli*. *Environ Sci Technol* 42(13):4927–4933
- Lee J, Eastal AJ, Pal U, Bhattacharyya D (2009) Evolution of ZnO nanostructures in sol–gel synthesis. *Curr Appl Phys* 9(4):792–796
- Lee CL, Lee HY, Tseng KH, Hong PA, Jou CJG (2011) Enhanced dechlorination of chlorobenzene by microwave-induced zero-valent iron: particle effects and activation energy. *Environ Chem Lett* 9(3):355–359
- Lee HJ, Song JY, Kim BS (2013) Biological synthesis of copper nanoparticles using *Magnolia kobus* leaf extract and their antibacterial activity. *J Chem Technol Biot* 88(11):1971–1977
- Li XQ, Zhang WX (2006) Iron nanoparticles: the core-shell structure and unique properties for Ni (II) sequestration. *Langmuir* 22(10): 4638–4642
- Li SM, Jia N, Ma MG, Zhang Z, Liu QH, Sun RC (2011) Cellulose-silver nanocomposites: microwave-assisted synthesis, characterization, their thermal stability, and antimicrobial property. *Carbohydr Polym* 86(2):441–447
- Li Y, Ma H, Ren B, Li T (2013) Simultaneous adsorption and degradation of Cr (VI) and Cd (II) ions from aqueous solution by silica-coated Fe₀ nanoparticles. *J Anal Methods Chem*
- Liang SC, Tan XY, Luxenberg DP, Karim R, Dunussi-Joannopoulos K, Collins M, Fouser LA (2006) Interleukin (IL)-22 and IL-17 are coexpressed by Th17 cells and cooperatively enhance expression of antimicrobial peptides. *J Exp Med* 203(10):2271–2279
- Lim TT, Feng J, Zhu BW (2007) Kinetic and mechanistic examinations of reductive transformation pathways of brominated methanes with nano-scale Fe and Ni/Fe particles. *Water Res* 41(4):875–883
- Lipovsky A, Nitzan Y, Lubart R (2008) A possible mechanism for visible light-induced wound healing. *Lasers Surg Med* 40(7):509–514
- Mahdavi M, Namvar F, Ahmad MB, Mohamad R (2013) Green biosynthesis and characterization of magnetic iron oxide (Fe₃O₄) nanoparticles using seaweed (*Sargassum muticum*) aqueous extract. *Molecules* 18(5):5954–5964
- Mahdavian AR, Mirrahimi MAS (2010) Efficient separation of heavy metal cations by anchoring polyacrylic acid on superparamagnetic magnetite nanoparticles through surface modification. *Chem Eng J* 159(1):264–271
- Malarkodi C, Rajeshkumar S, Vanaja M, Paulkumar K, Gnanajobitha G, Annadurai G (2013) Eco-friendly synthesis and characterization of gold nanoparticles using *Klebsiella pneumoniae*. *J Nanostruct Chem* 3(1):1–7
- Mallikarjuna K, Narasimha G, Dillip GR, Praveen B, Shreedhar B, Lakshmi CS, Raju BDP (2011) Green synthesis of silver nanoparticles using *Ocimum* leaf extract and their characterization. *Dig J Nanomater Biostruct* 6(1):181–186

- Martin PM, Good MS, Johnston JW, Posakony GJ, Bond LJ, Crawford SL (2000) Piezoelectric films for 100-MHz ultrasonic transducers. *Thin Solid Films* 379(1):253–258
- Masala O, Seshadri R (2004) Synthesis routes for large volumes of nanoparticles. *Annu Rev Mater Res* 34:41–81
- Mashrai A, Khanam H, Aljawfi RN (2013) Biological synthesis of ZnO nanoparticles using *C. albicans* and studying their catalytic performance in the synthesis of steroidal pyrazolines. *Arabian J Chem*. <http://dx.doi.org/10.1016/j.arabjc.2013.05.004>
- Mazumdar H, Haloi N (2011) A study on biosynthesis of iron nanoparticles by *Pleurotus sp.* *J Microbiol Biotechnol Res* 1(3):39–49
- McHenry ME, Laughlin DE (2000) Nano-scale materials development for future magnetic applications. *Acta Mater* 48(1):223–238
- Mehta SK, Singh K, Umar A, Chaudhary GR, Singh S (2012) Ultra-high sensitive hydrazine chemical sensor based on low-temperature grown ZnO nanoparticles. *Electrochim Acta* 69:128–133
- Mezni A, Kouki F, Romdhane S, Warot-Fonrose B, Joulié S, Mlayah A, Smiri LS (2012) Facile synthesis of ZnO nanocrystals in polyol. *Mater Lett* 86:153–156
- Mishra AN, Bhadauria S, Gaur MS, Pasricha R (2010) Extracellular microbial synthesis of gold nanoparticles using fungus *Hormoconis resinae*. *Metals Mater Soc* 62(11):45–48
- Mishra A, Tripathy SK, Wahab R, Jeong SH, Hwang I, Yang YB, Yun SI (2011) Microbial synthesis of gold nanoparticles using the fungus *Penicillium brevicompactum* and their cytotoxic effects against mouse mayo blast cancer C2C12 cells. *Appl Microbiol Biotechnol* 92(3):617–630
- Modi S, Pathak B, Fulekar MH (2015) Microbial synthesized silver nanoparticles for decolorization and biodegradation of azo dye compound. *J. Environ Nanotechnol* 4(2):37–46
- Mohamed YM, Azzam AM, Amin BH, Safwat NA (2015) Mycosynthesis of iron nanoparticles by *Alternaria alternata* and its antibacterial activity. *Afr J Biotechnol* 14(14):1234–1241
- Moore AM, De Leon CH, Young TM (2003) Rate and extent of aqueous perchlorate removal by iron surfaces. *Environ Sci Technol* 37(14):3189–3198
- Morones JR, Elechiguerra JL, Camacho A, Holt K, Kouri JB, Ramírez JT, Yacaman MJ (2005) The bactericidal effect of silver nanoparticles. *Nanotechnology* 16(10):2346
- Naja G, Halasz A, Thiboutot S, Ampleman G, Hawari J (2008) Degradation of hexahydro-1, 3, 5-trinitro-1, 3, 5-triazine (RDX) using zerovalent iron nanoparticles. *Environ Sci Technol* 42(12):4364–4370
- Namvar F, Azizi S, Ahmad MB, Shameli K, Mohamad R, Mahdavi M, Tahir PM (2015) Green synthesis and characterization of gold nanoparticles using the marine macroalgae *Sargassum muticum*. *Res Chem Intermed* 41(8):5723–5730
- Nanda A, Saravanan M (2009) Biosynthesis of silver nanoparticles from *Staphylococcus aureus* and its antimicrobial activity against MRSA and MRSE. *Nanomed Nanotechnol Biol Med* 5(4):452–456
- Narayanan KB, Sakthivel N (2010) Biological synthesis of metal nanoparticles by microbes. *Adv Colloid Interface Sci* 156(1):1–13
- Narayanan KB, Sakthivel N (2011) Synthesis and characterization of nano-gold composite using *Cylindrocodium floridanum* and its heterogeneous catalysis in the degradation of 4-nitrophenol. *J Hazard Mater* 189(1):519–525
- Nasrollahzadeh M, Sajadi SM, Maham M (2015) *Tamarix gallica* leaf extract mediated novel route for green synthesis of CuO nanoparticles and their application for N-arylation of nitrogen-containing heterocycles under ligand-free conditions. *RSC Adv* 5(51):40628–40635
- Nehru LC, Swaminathan V, Sanjeeviraja C (2012) Rapid synthesis of nanocrystalline ZnO by a microwave-assisted combustion method. *Powder Technol* 226:29–33
- Njagi EC, Huang H, Stafford L, Genuino H, Galindo HM, Collins JB, Suib SL (2010) Biosynthesis of iron and silver nanoparticles at room temperature using aqueous sorghum bran extracts. *Langmuir* 27(1):264–271

- Noruzi M, Zare D, Khoshnevisan K, Davoodi D (2011) Rapid green synthesis of gold nanoparticles using *Rosa hybrida* petal extract at room temperature. *Spectrochim Acta, Part A* 79(5):1461–1465
- Pal B, Sharon M (2002) Enhanced photocatalytic activity of highly porous ZnO thin films prepared by sol–gel process. *Mater Chem Phys* 76(1):82–87
- Pang S, Hernandez Y, Feng X, Müllen K (2011) Graphene as transparent electrode material for organic electronics. *Adv Mater (Weinheim, Ger)* 23(25):2779–2795
- Panigrahi S, Kundu S, Ghosh S, Nath S, Pal T (2004) General method of synthesis for metal nanoparticles. *J Nanopart Res* 6(4):411–414
- Pardeshi SK, Patil AB (2009) Solar photocatalytic degradation of resorcinol a model endocrine disrupter in water using zinc oxide. *J Hazard Mater* 163(1):403–409
- Park Y, Hong YN, Weyers A, Kim YS, Linhardt RJ (2011) Polysaccharides and phytochemicals: a natural reservoir for the green synthesis of gold and silver nanoparticles. *IET Nanobiotechnol* 5(3):69–78
- Perez-Gonzalez T, Jimenez-Lopez C, Neal AL, Rull-Perez F, Rodriguez-Navarro A, Fernandez-Vivas A, Iañez-Pareja E (2010) Magnetite biomineralization induced by *Shewanella oneidensis*. *Geochim Cosmochim Acta* 74(3):967–979
- Philip D, Unni C (2011) Extracellular biosynthesis of gold and silver nanoparticles using Krishna tulsi (*Ocimum sanctum*) leaf. *Physica E* 43(7):1318–1322
- Phumying S, Labuayai S, Thomas C, Amornkitbamrung V, Swatsitang E, Maensiri S (2013) *Aloe vera* plant-extracted solution hydrothermal synthesis and magnetic properties of magnetite (Fe₃O₄) nanoparticles. *Appl Phys A* 111(4):1187–1193
- Pissuwan D, Valenzuela SM, Cortie MB (2006) Therapeutic possibilities of plasmonically heated gold nanoparticles. *Trends Biotechnol* 24(2):62–67
- Pradeep T (2009) Noble metal nanoparticles for water purification: a critical review. *Thin Solid Films* 517(24):6441–6478
- Prasad K, Jha AK (2009) ZnO nanoparticles: synthesis and adsorption study. *Nat Sci* 1(02):129
- Prasad TN, Kambala VSR, Naidu R (2013) Phyconanotechnology: synthesis of silver nanoparticles using brown marine algae *Cystophora moniliformis* and their characterisation. *J Appl Phycol* 25(1):177–182
- Prathna TC, Chandrasekaran N, Raichur AM, Mukherjee A (2011) Biomimetic synthesis of silver nanoparticles by *Citrus limon* (lemon) aqueous extract and theoretical prediction of particle size. *Colloids Surfs B* 82(1):152–159
- Priya MM, Selvi BK, Paul JA (2011) Green synthesis of silver nanoparticles from the leaf extracts of *Euphorbia hirta* and *Nerium indicum*. *Digest J Nanomater Biostruct (DJNB)* 6(2)
- Rajeshkumar S, Kannan C, Annadurai G (2012) Green synthesis of silver nanoparticles using marine brown algae *Turbinaria conoides* and its antibacterial activity. *Int J Pharma Bio Sci* 3(4):502–510
- Rajiv P, Rajeshwari S, Venkatesh R (2013) Bio-Fabrication of zinc oxide nanoparticles using leaf extract of *Parthenium hysterophorus* L. and its size-dependent antifungal activity against plant fungal pathogens. *Spectrochim Acta, Part A* 112:384–387
- Ramanathan R, O'Mullane AP, Parikh RY, Smooker PM, Bhargava SK, Bansal V (2010) Bacterial kinetics-controlled shape-directed biosynthesis of silver nanoplates using *Morganella psychrotolerans*. *Langmuir* 27(2):714–719
- Ramanathan R, Bhargava SK, Bansal V (2011) Biological synthesis of copper/copper oxide nanoparticles. *Chemca Conference* 466. www.conference.net.au/chemeca2011/papers/466.pdf
- Ryu A, Jeong SW, Jang A, Choi H (2011) Reduction of highly concentrated nitrate using nanoscale zero-valent iron: effects of aggregation and catalyst on reactivity. *Appl Catal B* 105(1):128–135
- Saif Hasan S, Singh S, Parikh RY, Dharne MS, Patole MS, Prasad BLV, Shouche YS (2008) Bacterial synthesis of copper/copper oxide nanoparticles. *J Nanosci Nanotechnol* 8(6):3191–3196

- Salvadori MR, Lepre LF, Ando RA, do Nascimento CAO, Correia B (2013) Biosynthesis and uptake of copper nanoparticles by dead biomass of *Hypocrea lixii* isolated from the metal mine in the Brazilian Amazon region. PLoS One 8(11):e80519
- Sangeetha N, Kumaraguru AK (2014) Antitumor effects and characterization of biosynthesized iron oxide nanoparticles using seaweeds of gulf of mannar antitumor effects and characterization of biosynthesized iron oxide nanoparticles using seaweeds of gulf of mannar. Int J Pharm Pharm Sci 7(2):469–476
- Sangeetha G, Rajeshwari S, Venkatesh R (2011) Green synthesis of zinc oxide nanoparticles by *Aloe barbadensis miller* leaf extract: structure and optical properties. Mater Res Bull 46(12):2560–2566
- Sanna V, Pala N, Alzari V, Nuvoli D, Carcelli M (2016) ZnO nanoparticles with high degradation efficiency of organic dyes under sunlight irradiation. Mater Lett 162:257–260
- Sanpui P, Murugadoss A, Prasad PD, Ghosh SS, Chattopadhyay A (2008) The antibacterial properties of a novel chitosan–Ag–nanoparticle composite. Int J Food Microbiol 124(2):142–146
- Santornchot P, Satapanajaru T, Comfort SD (2010) Application of nano-zero valent iron for treating metolachlor in aqueous solution. World Acad Sci Eng Technol 48:625–628
- Satapanajaru T, Anurakpongsoatn P, Pengthamkeerati P, Boparai H (2008) Remediation of atrazine-contaminated soil and water by nano zerovalent iron. Water Air Soil Pollut 192(1–4):349–359
- Sathishkumar P, Mangalaraja RV, Anandan S, Ashokkumar M (2013) Photocatalytic degradation of ternary dye mixture in aqueous environment using gold nanoparticles loaded amino and mercapto functionalized TiMCM-41 nanocatalysts in the presence of visible light. Sep Purif Technol 102:67–74
- Sawle BD, Salimath B, Deshpande R, Bedre MD, Prabhakar BK, Venkataraman A (2016) Biosynthesis and stabilization of Au and Au–Ag alloy nanoparticles by fungus, *Fusarium semitectum*. Sci Tech Adv, Mater
- Seager R, Ting M, Held I, Kushnir Y, Lu J, Vecchi G, Li C (2007) Model projections of an imminent transition to a more arid climate in southwestern North America. Science 316(5828):1181–1184
- Selvakumar P, Viveka S, Prakash S, Jasminebeaula S, Uloganathan R (2012) Antimicrobial activity of extracellularly synthesized silver nanoparticles from marine derived *Streptomyces rochei*. Int J Pharm Biol Sci 3:188–197
- Sen K, Sinha P, Lahiri S (2011) Time dependent formation of gold nanoparticles in yeast cells: a comparative study. Biochem Eng J 55(1):1–6
- Senapati S, Syed A, Moez S, Kumar A, Ahmad A (2012) Intracellular synthesis of gold nanoparticles using alga *Tetraselmis kochinensis*. Mater Lett 79:116–118
- Shahwan T, Sirriah SA, Nairat M, Boyacı E, Eroğlu AE, Scott TB, Hallam KR (2011) Green synthesis of iron nanoparticles and their application as a Fenton-like catalyst for the degradation of aqueous cationic and anionic dyes. Chem Eng J 172(1):258–266
- Shantkriti S, Rani P (2014) Biological synthesis of copper nanoparticles using *Pseudomonas fluorescens*. Int J Curr Microbiol App Sci 3(9):374–383
- Sharma NC, Sahi SV, Nath S, Parsons JG, Gardea-Torresde JL, Pal T (2007) Synthesis of plant-mediated gold nanoparticles and catalytic role of biomatrix-embedded nanomaterials. Environ Sci Technol 41(14):5137–5142
- Sharma N, Pinnaka AK, Raje M, Ashish FNU, Bhattacharyya MS, Choudhury AR (2012) Exploitation of marine bacteria for production of gold nanoparticles. Microb Cell Fact 11(1):1
- Sharma B, Purkayastha DD, Hazra S, Thajamanbi M, Bhattacharjee CR, Ghosh NN, Rout J (2014) Biosynthesis of fluorescent gold nanoparticles using an edible freshwater red alga, *Lemanea fluviatilis* (L.) C. Ag and antioxidant activity of biomatrix loaded nanoparticles. Bioprocess Biosyst Eng 37(12):2559–2565
- Sharma G, Kr DG, Jasuja ND, Joshi S (2015a). *Pterocarpus marsupium* derived phyto-synthesis of copper oxide nanoparticles and their antimicrobial activities. J Microb Biochem Technol

- Sharma JK, Akhtar MS, Ameen S, Srivastava P, Singh G (2015b) Green synthesis of CuO nanoparticles with leaf extract of *Calotropis gigantea* and its dye-sensitized solar cells applications. *J Alloys Compd* 632:321–325
- Sheikhloo Z, Salouti M, Katirae F (2011) Biological synthesis of gold nanoparticles by fungus *Epicoccum nigrum*. *J Cluster Sci* 22(4):661–665
- Singaravelu G, Arockiamary JS, Kumar VG, Govindaraju K (2007) A novel extracellular synthesis of monodisperse gold nanoparticles using marine alga, *Sargassum wightii* Greville. *Colloids Surf B* 57(1):97–101
- Singh A, Patil R, Anand A, Milani P, Gade WN (2010) Biological synthesis of copper oxide nanoparticles using *Escherichia coli*. *Curr Nanosci* 6(4):365–369
- Singh RP, Magesh S, Rakkiyappan C (2011) Formation of fenugreek (*Trigonella foenum-graecum*) extract mediated Ag nanoparticles: mechanism and applications. *Int J Bioeng Sci Technol* 2(3):64–73
- Singh M, Kalaivani R, Manikandan S, Sangeetha N, Kumaraguru AK (2013a) Facile green synthesis of variable metallic gold nanoparticle using *Padina gymnospora*, a brown marine macroalga. *Appl Nanosci* 3(2):145–151
- Singh N, Singh SP, Gupta V, Yadav HK, Ahuja T, Tripathy SS (2013b) A process for the selective removal of arsenic from contaminated water using acetate functionalized zinc oxide nanomaterials. *Environ Prog Sustain Energy* 32(4):1023–1029
- Sinha T, Ahmaruzzaman M (2015) Green synthesis of copper nanoparticles for the efficient removal (degradation) of dye from aqueous phase. *Environ Sci Pollut Res* 22(24):20092–20100
- Sinha SN, Paul D, Halder N, Sengupta D, Patra SK (2015) Green synthesis of silver nanoparticles using fresh water green alga *Pithophora oedogonia* (Mont.) Wittrock and evaluation of their antibacterial activity. *Appl Nanosci* 5(6):703–709
- Sivaraj R, Rahman PK, Rajiv P, Salam HA, Venckatesh R (2014a) Biogenic copper oxide nanoparticles synthesis using *Tabernaemontana divaricate* leaf extract and its antibacterial activity against urinary tract pathogen. *Spectrochim Acta, Part A* 133:178–181
- Sivaraj R, Rahman PK, Rajiv P, Narendhran S, Venckatesh R (2014b) Biosynthesis and characterization of *Acalypha indica* mediated copper oxide nanoparticles and evaluation of its antimicrobial and anticancer activity. *Spectrochim Acta, Part A* 129:255–258
- Smuleac V, Varma R, Sikdar S, Bhattacharyya D (2011) Green synthesis of Fe and Fe/Pd bimetallic nanoparticles in membranes for reductive degradation of chlorinated organics. *J Membr Sci* 379(1):131–137
- Song H, Carraway ER (2005) Reduction of chlorinated ethanes by nanosized zero-valent iron: kinetics, pathways, and effects of reaction conditions. *Environ Sci Technol* 39(16):6237–6245
- Song JY, Jang HK, Kim BS (2009) Biological synthesis of gold nanoparticles using *Magnolia kobus* and *Diopyros kaki* leaf extracts. *Process Biochem* 44(10):1133–1138
- Soomro RA, Nafady A (2015) Catalytic reductive degradation of methyl orange using air resilient copper nanostructures. *J Nanomater* 2015:120
- Srivastava V, Gusain D, Sharma YC (2013) Synthesis, characterization and application of zinc oxide nanoparticles (n-ZnO). *Ceram Int* 39(8):9803–9808
- Subbaiya R, Shiyamala M, Revathi K, Pushpalatha R, Selvam MM (2014) Biological synthesis of silver nanoparticles from *Nerium oleander* and its antibacterial and antioxidant property. *Int J Curr Microbiol App Sci* 3(1):83–87
- Sundaram PA, Augustine R, Kannan M (2012) Extracellular biosynthesis of iron oxide nanoparticles by *Bacillus subtilis* strains isolated from rhizosphere soil. *Biotechnol Bioprocess Eng* 17(4):835–840
- Sundaramurthy N, Parthiban C (2015) Biosynthesis of copper oxide nanoparticles using *Pyrus pyrifolia* leaf extract and evolve the catalytic activity. *Int Res J Eng Technol* 2:332–337
- Suresh AK, Pelletier DA, Wang W, Broich ML, Moon JW, Gu B, Doktycz MJ (2011) Biofabrication of discrete spherical gold nanoparticles using the metal-reducing bacterium *Shewanella oneidensis*. *Acta Biomater* 7(5):2148–2152

- Suvith VS, Philip D (2014) Catalytic degradation of methylene blue using biosynthesized gold and silver nanoparticles. *Spectrochim Acta, Part A* 118:526–532
- Swihart MT (2003) Vapor-phase synthesis of nanoparticles. *Curr Opin Colloid Interface Sci* 8 (1):127–133
- Tratnyek PG, Johnson RL (2006) Nanotechnologies for environmental cleanup. *Nano Today* 1 (2):44–48
- Usha R, Prabu E, Palaniswamy M, Venil CK, Rajendran R (2010) Synthesis of metal oxide nano particles by *Streptomyces* sp. for development of antimicrobial textiles. *Global J Biotechnol Biochem* 5(3):153–160
- Vahabi K, Mansoori GA, Karimi S (2011) Biosynthesis of silver nanoparticles by fungus *Trichoderma reesei*. *Insci J* 1(1):65–79
- Varshney R, Bhadauria S, Gaur MS, Pasricha R (2010) Characterization of copper nanoparticles synthesized by a novel microbiological method. *Jom* 62(12):102–104
- Venkateswarlu S, Rao YS, Balaji T, Prathima B, Jyothi NVV (2013) Biogenic synthesis of Fe₃O₄ magnetic nanoparticles using plantain peel extract. *Mater Lett* 100:241–244
- Verma VC, Kharwar RN, Gange AC (2010a) Biosynthesis of antimicrobial silver nanoparticles by the endophytic fungus *Aspergillus clavatus*. *Nanomedicine* 5(1):33–40
- Verma VC, Singh SK, Solanki R, Prakash S (2010b) Biofabrication of anisotropic gold nanotriangles using extract of endophytic *Aspergillus clavatus* as a dual functional reductant and stabilizer. *Nanoscale Res Lett* 6(1):1
- Vidya C, Hiremath S, Chandrababha MN, Antonyraj I, Gopal V, Jai A, Bansal K (2013) Green synthesis of ZnO nanoparticles by *Calotropis gigantea*. *Int J Curr Eng Technol* 1:118–120
- Vigneshwaran N, Kumar S, Kathe AA, Varadarajan PV, Prasad V (2006) Functional finishing of cotton fabrics using zinc oxide-soluble starch nanocomposites. *Nanotechnology* 17(20):5087
- Vijayakumar M, Priya K, Nancy FT, Noorlidah A, Ahmed ABA (2013) Biosynthesis, characterisation and anti-bacterial effect of plant-mediated silver nanoparticles using *Artemisia nilagirica*. *Ind Crop Prod* 41:235–240
- Wang ZL, Kong XY, Ding Y, Gao P, Hughes WL, Yang R, Zhang Y (2004) Semiconducting and piezoelectric oxide nanostructures induced by polar surfaces. *Adv Funct Mater* 14(10):943–956
- Wang Z, Fang C, Megharaj M (2014) Characterization of iron-polyphenol nanoparticles synthesized by three plant extracts and their Fenton oxidation of azo dye. *ACS Sustain Chem Eng* 2(4):1022–1025
- Wei YT, Wu SC, Yang SW, Che CH, Lien HL, Huang DH (2012) Biodegradable surfactant stabilized nanoscale zero-valent iron for in situ treatment of vinyl chloride and 1,2-dichloroethane. *J Hazard Mater* 211:373–380
- Wu SH, Mou CY, Lin HP (2013) Synthesis of mesoporous silica nanoparticles. *Chem Soc Rev* 42 (9):3862–3875
- Xiong HM (2013) ZnO nanoparticles applied to bioimaging and drug delivery. *Adv Mater (Weinheim, Ger)* 25(37):5329–5335
- Yamini SG, Banu F, Ezhilarasan A (2011) Sahadevan. Green Synthesis of Silver Nanoparticles from Cleome Viscosa, *Synth Antimicrob Act*, p 5
- Yang C, Xu C, Wang X (2012) ZnO/Cu nanocomposite: a platform for direct electrochemistry of enzymes and biosensing applications. *Langmuir* 28(9):4580–4585
- Zelmanov G, Semiat R (2008) Iron (3) oxide-based nanoparticles as catalysts in advanced organic aqueous oxidation. *Water Res* 42(1):492–498
- Zhao J, Wang L (2011) Degradation of Rhodamine B in aqueous solution by the UV/ZnO photocatalytic process. In: 2011 international conference on materials for renewable energy and environment
- Zhou H, Fan T, Han T, Li X, Ding J, Zhang D, Ogawa H (2009) Bacteria-based controlled assembly of metal chalcogenide hollow nanostructures with enhanced light-harvesting and photocatalytic properties. *Nanotechnology* 20(8):085603

Bioremediation and Sustainable Technologies for
Cleaner Environment

Prashanthi, M.; Sundaram, R.; Jeyaseelan, A.; Kaliannan,
T. (Eds.)

2017, XI, 358 p. 136 illus., 92 illus. in color., Hardcover

ISBN: 978-3-319-48438-9