

**substance:**  $\text{Hf}_2\text{Se}_3$

**property:** crystal structure, physical properties

colour: black

58M

**resistivity**

$\rho$	$6\ \Omega\ \text{cm}$	n-type, polycrystalline sample
--------	------------------------	-----------------------------------

**Seebeck coefficient**

$S$	$-200\ \mu\text{V}\ \text{K}^{-1}$	n-type, polycrystalline sample
-----	------------------------------------	-----------------------------------

**References:**

58M     McTaggart, F. K.: Aust. J. Chem. 11 (1958) 471.