

**substance: OsSi<sub>2</sub>**

**property: space group, lattice parameters**

(RT values)

**space group:** D<sub>2h</sub><sup>18</sup> – Cmca; Z = 16

**lattice parameters**

<i>a</i> [Å]	<i>b</i> [Å]	<i>c</i> [Å]	Ref.
10.1496	8.1168	8.2230	70E

**References:**

70E Engström, I.: Acta Chem. Scand. 24 (1970) 2117.