

substance: OsPS
property: physical properties

energy gap

E_g	$> 1.4 \text{ eV}$	RT	from diffuse reflectance	63H
-------	--------------------	----	--------------------------	-----

thermoelectric power

S	$\approx -1000 \text{ } \mu\text{V K}^{-1}$	$T = 300 \text{ K}$	sintered sample	63H
-----	---	---------------------	-----------------	-----

far infrared absorption: for spectrum in the range $60\ldots 550 \text{ cm}^{-1}$, see [83L].

For structure, chemical bond and comparative tables on crystallographic and physical properties of transition metal-V-VI compounds, see documents , , , .

References:

- 63H Hulliger, F.: Nature (London) 201 (1963) 381.
83L Lutz, M. D., Schneider, G., Kliche, G.: Phys. Chem. Minerals 9 (1983) 109.