

substance: OsAsTe
property: physical properties

thermoelectric power

S	$+ 250 \mu\text{V K}^{-1}$	$T = 300 \text{ K}$	sintered sample	63H
-----	----------------------------	---------------------	-----------------	-----

magnetic susceptibility

χ_m	$114 \cdot 10^{-6} \text{ cm}^3 \text{ mol}^{-1}$	$T = 295 \text{ K}$	χ in CGS-emu, powdered sample; Gouy method, $B < 1 \text{ T}$	63H
----------	---------------------------------------------------	---------------------	-----------------------------------------------------------------------	-----

far infrared absorption: for spectrum in the range $50 \dots 500 \text{ cm}^{-1}$, see [83L].

For structure, chemical bond and comparative tables on crystallographic and physical properties of transition metal-V-VI compounds, see documents , , , .

References:

- 63H Hulliger, F.: Nature (London) 201 (1963) 381.
83L Lutz, M. D., Schneider, G., Kliche, G.: Phys. Chem. Minerals 9 (1983) 109.