

substance: CoSbSe

property: physical properties

thermoelectric power

S $-25 \mu\text{V K}^{-1}$ $T = 300 \text{ K}$ on sintered sample 80H

A 30 min treatment at $T = 1870 \text{ K}$, $p = 60 \text{ kbar}$ did not transform the marcasite structure [75H].

For structure, chemical bond and comparative tables on crystallographic and physical properties of transition metal-V-VI compounds, see documents , , , .

References:

- 75H Henry, R., Steger, J., Nahigian, H., Wold, A.: Inorg. Chem 14 (1975) 2915.
80H Hulliger, F.: unpublished 1980.