

substance: PdO

property: magnetic properties

magnetic susceptibility

χ_m	$-4 \cdot 10^{-6} \text{ cm}^3 \text{ mol}^{-1}$	$T = 295 \text{ K}$	χ_m in CGS-emu	65H
	$-2 \cdot 10^{-6} \text{ cm}^3 \text{ mol}^{-1}$	$T = 80 \text{ K}$		

References:

65H Hulliger, F.: J. Phys. Chem. Solids 26 (1965) 639.