

substance: OsSe₂

property: crystal structure, physical properties

(The references in the last column refer to all data of this document)

lattice parameters

a	5.945 Å	structure: pyrite, C2, T _h ⁶ – Pa3	63H, 71L
-----	---------	--	-------------

Seebeck coefficient

S	– 80 μV K ^{–1}	n-type, poly-crystalline sample	diamagnetic
-----	-------------------------	---------------------------------	-------------

References:

- 63H Hulliger, F.: Nature (London) 200 (1963) 1064.
71L Landolt-Börnstein (New Series), ed.: K. H. Hellwege, Vol. III/6, Springer Verlag: Berlin, Heidelberg, New York 1971.