

**substance:  $\text{Sm}_3\text{Te}_4$**

**property: crystal structure**

**crystal structure**

cubic ( $\text{Th}_3\text{P}_4$ -type,  $T_d^6 - I\bar{4}3d$ )

**lattice parameters**

$a$  9.506 Å

65F

**References:**

- 65F     Flahaut, J., Guittard, M., Patrie, M., Pardo, M. P., Golabi, S. M., Domange, L.: Acta. Cryst. 19 (1965) 14.