

substance: Tm₂O₃

property: crystal structure, physical properties

Tm₂O₃ [88L]

structure: cubic

activation energy for conductivity

E_A	2.84 eV	$T = 800 \dots 1200 \text{ K}$,	energy band diagram: Fig. 1
		val. band-4f ¹³	

conductivity

σ	$2.96 \cdot 10^2 \text{ } \Omega^{-1} \text{ m}^{-1}$	p-type
----------	---	--------

mobility

μ_p	$0.426 \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$	$T = 900 \text{ K}$
---------	--	---------------------

References:

88L Lal, H.B., Kanchan Gaur: J. Mater. Sci. 23 (1988) 919.

Fig. 1.

Energy band diagram for rare-earth sesquioxides [88L].

