

substance: WO₃

property: magnetic properties

magnetic susceptibility

χ_m	$-1.7 \cdot 10^{-10} \text{ m}^3 \text{ mol}^{-1}$	RT	χ_m in SI units	75S
----------	----------------------------------------------------	----	----------------------	-----

References:

75S Snare, J., Karner, R., Leftkowitz, J., Friedberg, C. B., Ruvalds, J.: Bull. Am. Phys. Soc. 23 (1978) 309.