
No. 1B-b11 **Pb(Ni_{1/2}Te_{1/2})O₃**
(*M* = 348.3)

1a	Dielectric property of Pb(Ni _{1/2} Te _{1/2})O ₃ was reported by Politova and Venevtsev.	73Pol
b	Crystal system: perovskite cubic at RT.	73Pol
3a	<i>a</i> = 7.97 Å at RT.	73Pol
5a	Dielectric constant: κ_{\max} at $\Theta \approx -30$ °C (<i>f</i> = 1 kHz).	73Pol

Reference

- 73Pol Politova, E.D., Venevtsev, Yu.N.: Dokl. Akad. Nauk SSSR **209** (1973) 838; Sov. Phys. Dokl. (English Transl.) **18** (1973) 264.