
No. 1B-c25 $\text{Pb}(\text{Fe}_{1/2}\text{W}_{1/2})\text{O}_3$
($M = 375.0$)

1a A synthesis of $\text{Pb}(\text{Fe}_{1/2}\text{W}_{1/2})\text{O}_3$ with perovskite structure was reported by Venevtsev et al.. 64Ven

12 The magnetic measurements confirmed the presence of the spinel phase in a sample of this composition. 65Rog

References

- 64Ven Venevtsev, Yu.N., Roginskaya, Yu.E., Viskov, A.S., Ivanova, V.V., Tomashpol'skii, Yu.Ya., Shvorneva, L.I., Kapyshev, A.G., Teverpvsckii, A.Yu., Zhdanov, G.S.: Dokl. Akad. Nauk SSSR **158** (1964) 86; Sov. Phys. Dokl. (English Transl.) **9** (1965) 751.
- 65Rog Roginskaya, Yu.E., Venevtsev, Yu.N., Zhdanov, G.S.: Zh. Eksp. Teor. Fiz. **48** (1965) 1224; Sov. Phys. JETP (English Transl.) **21** (1965) 817.