
No. 1B-e4 $\text{Pb}(\text{Sc}_{2/3}\text{W}_{1/3})\text{O}_3$
($M = 346.5$)

1a A synthesis of $\text{Pb}(\text{Sc}_{2/3}\text{W}_{1/3})\text{O}_3$ with perovskite structure was reported by Tomashpol'skii and Venevtsev in 1965. 65Tom

5a Dielectric constant: κ_{max} at $\Theta \approx -12^\circ\text{C}$ ($f = 200\text{ kHz}$). 65Tom

Reference

65Tom Tomashpol'skii, Yu.Ya., Venevtsev, Yu.N.: Fiz. Tverd. Tela **7** (1965) 517; Sov. Phys. Solid State (English Transl.) **7** (1965) 412.