

---

**No. 1B-f1  $\text{Pb}(\text{Cd}_{4/9}\text{Nb}_{2/9}\text{W}_{1/3})\text{O}_3$**   
( $M = 387.1$ )

---

|    |   |       |
|----|---|-------|
| 1a | Dielectric anomaly in $\text{Pb}(\text{Cd}_{4/9}\text{Nb}_{2/9}\text{W}_{1/3})\text{O}_3$ was reported by Tomashpol'skii and Venevtsev in 1965. | 65Tom |
| b  | Crystal system: perovskite monoclinic at RT.  | 65Tom |
| 3a | $a = c = 4.133 \text{ \AA}$ , $b = 4.083 \text{ \AA}$ , $\beta = 90^\circ 38'$ at RT.   | 65Tom |
| 5a | Dielectric constant jumps appreciably at $495^\circ\text{C}$ .  | 65Tom |

---

**Reference**

- 65Tom Tomashpol'skii, Yu.Ya., Venevtsev, Yu.N.: Fiz. Tverd. Tela **7** (1965) 517; Sov. Phys. Solid State (English Transl.) **7** (1965) 412.