
No. 1B-f2 $\text{Pb}(\text{Sc}_{5/9}\text{Nb}_{1/3}\text{W}_{1/9})\text{O}_3$
($M = 331.6$)

1a	Dielectric anomaly in $\text{Pb}(\text{Sc}_{5/9}\text{Nb}_{1/3}\text{W}_{1/9})\text{O}_3$ with perovskite structure was reported by Tomashpol'skii and Venevtsev in 1965.	65Tom
b	Crystal system: cubic at RT.	65Tom
3a	$a = 4.074 \text{ \AA}$ at RT.	65Tom
5a	Dielectric constant: κ_{max} at $\Theta \leq -170 \text{ }^\circ\text{C}$ ($f = 200 \text{ kHz}$).	65Tom

Reference

- 65Tom Tomashpol'skii, Yu.Ya., Venevtsev, Yu.N.: Fiz. Tverd. Tela **7** (1965) 517; Sov. Phys. Solid State (English Transl.) **7** (1965) 412.