

---

**No. 1B-b4  $\text{Ba}(\text{Mn}_{1/2}\text{Te}_{1/2})\text{O}_3$**   
( $M = 276.60$ )

---

1a	Dielectric property of $\text{Ba}(\text{Mn}_{1/2}\text{Te}_{1/2})\text{O}_3$ was reported by Politova and Venevtsev.	75Pol
b	Crystal system: perovskite pseudocubic at RT.	75Pol
3a	$a = 8.19 \text{ \AA}$ at RT.	75Pol
5a	Dielectric constant: $\kappa_{\text{max}}$ at $\Theta \approx 140^\circ\text{C}$ .	75Pol

---

**Reference**

75Pol     Politova, E.D., Venevtsev, Yu.N.: Mater. Res. Bull. **10** (1975) 319.