
No. 1B-c28 $\text{Pb}(\text{Sc}_{1/4}\text{Cr}_{1/4}\text{Nb}_{1/2})\text{O}_3$
($M = 325.9$)

1a	Ferroelectric property was reported by Tomashpolskii and Venevtsev in 1965.	65Tom
b	Crystal system: perovskite pseudocubic.	65Tom
3a	$a = 4.060 \text{ \AA}$.	65Tom
5a	Dielectric constant: κ_{max} at $\Theta_f \approx 57 \text{ }^\circ\text{C}$ ($f = 20 \text{ kHz}$).	65Tom

Reference

- 65Tom Tomashpol'skii, Yu.Ya., Venevtsev, Yu.N.: Fiz. Tverd. Tela **7** (1965) 517; Sov. Phys. Solid State (English Transl.) **7** (1965) 412.