

Table 23A-1-001. Ag_3AsS_3 (proustite). Elastic constants determined by Brillouin scattering measurements [81Smo], [73Zub]. $T = 295$ K.

$c_{\lambda\mu} [\cdot 10^{10} \text{ N m}^{-2}]$	81Smo	73Zub
c_{11}	5.95	5.70
c_{33}	3.975	3.64
c_{44}	0.997	0.90
c_{66}	1.389	1.26
c_{12}	3.171	—
c_{13}	2.965	—
c_{14}	0.018	—