

Table 23A-2-001. Ag₃SbS₃. Elastic constants determined by ultrasonic velocity measurements [81Oli].

$\lambda\mu$	11	12	13	14	33	44
$c_{\lambda\mu}^E [\cdot 10^{10} \text{ N m}^{-2}]$	5.27	2.63	0.49	−0.04	3.78	1.16
$c_{\lambda\mu}^D [\cdot 10^{10} \text{ N m}^{-2}]$	5.38	–	–	–	4.27	1.20
$s_{\lambda\mu}^E [\cdot 10^{-11} \text{ m}^2 \text{ N}^{-1}]$	2.54	−1.25	−0.17	0.14	2.69	8.63