

No. 35B-3 K(A,B)OGeO_4 (A, B = Ti, Nb, Sb, Ta)

1	$\text{KSb}_{1-x}\text{Nb}_x\text{OGeO}_4$: Solid solution region: $0 \leq x \leq 0.75$.	94But
	$\text{KTa}_{1-x}\text{Nb}_x\text{OGeO}_4$: Solid solution region: $0 \leq x \leq 0.75$.	94But
	Θ_f vs. x: Fig. 35B-3-001, Fig. 35B-3-002.	
3a	Lattice constants: Table 35B-3-001.	
9e	Nonlinear optical properties: Fig. 35B-3-003, Fig. 35B-3-004.	