

**No. 36A-3 NaCdPO<sub>4</sub>, Sodium cadmium phosphate***(M* = 230.37)

1a Ferroelectric hysteresis loop in NaCdPO <sub>4</sub> was observed by Elouadi et al. in 1984.			84Elo
b phase	II	I	84Elo
state	F		
crystal system	orthorhombic		
Θ[°C]	715		
T <sub>melt</sub> = 1210 °C.			84Elo
2a Crystal growth: flux method.			84Elo
5c P <sub>s</sub> = 1.7 · 10 <sup>-2</sup> C m <sup>-2</sup> at RT.			84Elo