
No. 35A-12 RbSnOPO_4 , Rubidium stannyl phosphate
($M = 315.149$)

1a	Orthorhombic, $\text{Pna}2_1\text{--}\text{C}_{2v}^9$ at RT.	89Phi
2a	Sample preparation: see Table 35B-5-001 in No. 35B-5.	
3a	Unit cell volume: see Table 35B-5-001 in No. 35B-5.	
9e	Nonlinear optical properties: see Table 35B-5-001 in No. 35B-5.	
