

**Table 35B-4-001.** KTi<sub>1-x</sub>Nb<sub>x</sub>OP<sub>1-x</sub>Ge<sub>x</sub>O<sub>4</sub>. Change of lattice constants with composition [94But].

Lattice parameters [Å]			
x	<i>a</i>	<i>b</i>	<i>c</i>
0	12.869(4)	6.375(2)	10.558(3)
0.25	12.962(5)	6.471(3)	10.661(4)
0.5	13.13(1)	6.540(5)	10.77(1)
0.75	13.26(1)	6.621(4)	10.90(1)
0.8	13.282(8)	6.624(4)	10.929(7)
0.85	13.303(6)	6.638(3)	10.950(4)