

No. 43B-5 $\text{K}_2\text{Mn}_2(\text{SO}_4)_3$ – $\text{Tl}_2\text{Mn}_2(\text{SO}_4)_3$

1a	θ of $\text{K}_{1.79}\text{Tl}_{0.19}\text{Mn}_2(\text{SO}_4)_3$: $-48\text{ }^\circ\text{C}$.	89Mar
2a	Sample preparation of $\text{K}_{2(1-x)}\text{Tl}_{2x}\text{Mn}_2(\text{SO}_4)_3$ in the range $0 \leq x \leq 1$: evaporation of aqueous solutions.	89Mar
3a	Unit cell parameters: Table 43B-5-001.	
6	Differential scanning calorimetry was performed.	89Mar