

Table 48A-1-001. $\text{K}_4\text{Me}(\text{CN})_6 \cdot 3\text{H}_2\text{O}$, $\text{K}_4\text{Me}(\text{CN})_6 \cdot 3\text{D}_2\text{O}$ (Me = Mn, Fe, Ru, Os). Ferroelectric transition temperature [60Wak2].

Me	H	D
	$\theta_f [^\circ\text{C}]$	
Mn	−40	—
Fe	−24.5	−18.0
Ru	−14.5	−7.3
Os	−2.4	1.8