

## Ac – Au (Actinium – Gold)

### Phase diagram

The solubility of Ac in (Au) amounts to  $10^{-2}$  to  $10^{-3}$  at% Ac (estimated by [68 Gul]).

### Reference

[68 Gul] Gulyaev, B.B., Dvorshkaya, G.F. : “Phase Diagrams of Metallic Systems”, Savitskii, E.M. (ed.), Nauka Publ., Moscow (1968) 267