

Ac – Cu (Actinium – Copper)

Phase diagram

On the basis of systematic considerations Gulyaev et al. [68 Gul] assumed an eutectic at $T \approx 1123$ K and $c_E \approx 92$ at% Cu.

Reference

- [68 Gul] Gulyaev, B.B., Dvorshkaya, G.F., in: "Phase Diagrams of Metallic Systems", Savitskii, E.M. (ed.), Nauka Publ., Moscow (1968) 267
- [Massalski] Massalski, T.B. (Editor-in-Chief) in: "Binary Alloy Phase Diagrams", second edition, The Materials Information Society, ASM International, Materials Park, Ohio (1992)