

Ag – Ra (Silver – Radium)

Phase diagram

As Okamoto in [Massalski] stated, Gulyaev et al. [68 Gul] have estimated a partial phase diagram with an eutectic point at 0.01 at% Ra and 1223 K. At this temperature a solubility of Ra in (Ag) is assumed to be 10^{-4} at%.

References

- [68 Gul] Gulyaev, B.B., Dvorshkaya, G.F., in: “Phase Diagrams of Metallic Systems”, Savitskii, E.M. (ed.), Nauka Publ., Moscow (1968) 267
- [Massalski] Massalski, T.B., (ed.): “Binary Alloy Phase Diagrams”, Second Edition, The Materials Information Society, ASM International, Materials Park, Ohio (1992)