

Am – Bi (Americium – Bismuth)

Crystal structure

An intermediate phase has been found by Roddy [74 Rod] in this system: AmBi. Its structure is cubic (NaCl-type) with

$$a = 0.6338 \text{ nm.}$$

Reference

[74 Rod] Roddy, J.W.: J. Inorg. Nucl. Chem. **36** (1974) 2531