

## **Au – Fr (Gold – Francium)**

### **Phase diagram**

Gulyaev et al. [68 Gul] have estimated that Fr is soluble in solid (Au) to about  $10^{-4}$  to  $10^{-5}$  at% Fr.

### **Reference**

[68 Gul] Gulyaev, B.B., Dvorshkaya, G.F., in: “Phase Diagrams of Metallic Systems”, Savitskii, E.M. (ed.), Akad. Nauk SSSR, (1968) 267