

## Au – Kr (Gold – Krypton)

### Phase diagram

Gulyaev et al. [68 Gul] have estimated the solubility of Kr in (Au). Their assumption:  $10^{-6}$  to  $10^{-7}$  at% Kr are soluble in (Au).

### Reference

- [68 Gul] Gulyaev, B.B., Dvorshkaya, G.F.: “Phase Diagrams of Metallic Systems”, Savitskii, E.M. (ed.), Akad. Nauk, SSSR (1968) 267